



PRIMEPAC

making it easy!



Carton Liner 635x375x660mm 25kg

GENERAL PRODUCT INFORMATION

Product:	Carton Liner 635x375x660mm 25kg
Code:	2347
Size:	0.012 mm(t) x 1010 mm(w) x 660 mm(l) x 187.5 mm(g)
Thickness:	0.012 mm \pm 0.003 mm
Width:	1010 mm \pm 20 mm
Length:	660 mm \pm 10 mm
Gusset:	187.5 mm
Seal line:	Bottom seal
Packing:	500pcs/ctn



0800 277 772



www.primepac.co.nz



sales@primepac.co.nz



L3 1/61 Constellation Drive, Rosedale, Auckland

Date of Issue: 21 September 2023

Carton Liner 25kg: 2347

PRODUCT SPECIFICATION

Product:	PLAIN HDPE GUSSETED BOTTOM SEAL GARBAGE BAG
Dimension:	0.012MM(T) X 1010MM(W) X 660MM(L) X 187.5MM(G)
Code:	2347
Test Date:	31/03/2023

Primepac confirms the raw materials (as per supplier declaration) and the formulation and manufacturing process of the mentioned product complies with the stated regulation below:

U.S. FDA Food Contact

This product meets the requirements for polyolefin resins intended for food packaging applications as described in the FDA olefin polymer regulations 21 CFR 177.1520(c)3.2a. The resin may be used in contact with all types of food as defined in 21 CFR 175.300 and 178.3910

European Union (EU) Food Contact

The monomer(s) and the additive(s) of this resin are listed in Commission Regulation (EU) No 10/2011 on plastic materials and articles intended to come into contact with food and all its Amendments.

DISCLAIMER: Although this product is not routinely tested for their presence, based on product composition knowledge these substances are not expected to be present. However, the fact that these substances are not intentionally used by Primepac and its suppliers in this product do not exclude that trace levels of these substances may be present as a result of specific characteristics of the raw materials and/or of the manufacturing process.



PRIMEPAC

making it easy!

PHYSICAL PROPERTIES

PROPERTIES	UNIT	SPECIFICATION	TEST METHOD
Thickness	mm	0.012 (\pm 0.003MM)	THICKNESS GAUGE
Width	mm	1010 (\pm 20MM)	MEASURING TAPE
Length	mm	660 (\pm 10MM)	MEASURING TAPE
Gusset	mm	187.5	MEASURING TAPE

MECHANICAL PROPERTIES

PROPERTIES	UNIT	SPECIFICATION		TEST METHOD
TENSILE STRENGTH (MD / TD)	MPa	36.52 / 22.94		THICKNESS GAUGE
ELONGATION (MD / TD)	%	261.28 / 468.89		MEASURING TAPE
SLIP LEVEL (DCOF/SCOF)	-	OUTER	INNER	MEASURING TAPE
		0.216 / 0.221 (HIGH SLIP)	0.231 / 0.234 (HIGH SLIP)	



0800 277 772



www.primepac.co.nz



sales@primepac.co.nz



L3 1/61 Constellation Drive, Rosedale, Auckland