



PRIMEPAC

making it easy!



2081 NEXWRAP MACHINE PALLET WRAP 12MU

PHYSICAL PROPERTIES	TEST METHOD	VALUE	UNIT
Width	Measurement Tape	500 (+/-5)	mm
Average Thickness	Thickness Gauge	(0.012) +/-0.001	mm
Ultimate Stretch Level	Inhouse Testing Method	> 380	%
Quality Test	Continuous 50m run stretched at 400%	Pass	
Tensile Strength	ASTM D 882	MD $\geq$ 30 TD $\geq$ 19	MPa
Elongation	ASTM D 882	MD $\geq$ 400 TD $\geq$ 490	%
Dart Impact	ASTM D 1709	$\geq$ 120	gm
Tear Strength	ASTM D 1922	MD $\geq$ 90 TD $\geq$ 350	gm



0800 277 772



www.primepac.co.nz



sales@primepac.co.nz



L3 1/61 Constellation Drive, Rosedale, Auckland