



PRIMEPAC

making it easy!

Woven Strapping belt production QC Report

Item name	G74	Material	Yarn	Test date	2025.08.26
Width:	19mm+0.7mm/-0.5mm		Thickness:	1.0±0.2mm	


Testing method



1. Surface



2. Hand tension test



3.Width



4. Thickness



5. Linear test



6. System test

Surface + Hands tension test

Method \ No.	1	2	3	4	5	Remarks
Surface	OK	OK	OK	OK	OK	Standard performance
Hands tension test	OK	OK	OK	OK	OK	

Width + Thickness + Linear strength test + System breaking strength test

Method \ No.	1	2	3	4	5	Average	Remarks
Width	19.24	19.20	19.18	19.14	19.18	19.19	Ambient temperature
Thicknes	1.08	1.10	1.08	1.10	1.08	1.09	
Breaking strength of linear test(830daN)	854	867	843	856	841	852	
System breaking strength test (1170daN) with buckle 1943P	1183	1208	1184	1197	1190	1192	

Elongation

Trial -No.	Elongatiat at 30%	Elongation at 50%	Elongation at 70%	Elongation at 100%	Remarks
Elongation test with self belt 10cm length	10.50	10.70	10.90	11.20	The test result should not be above 11.5cm

Note: Test results have 3% tolerance, pictures illustrate testing method.



0800 277 772



www.primepac.co.nz



sales@primepac.co.nz



L3 1/61 Constellation Drive, Rosedale, Auckland